

KUBRICKY CONSTRUCTION CORP.
269 BALLARD ROAD

WILTON, NY 12831
518 792-5864



KUBRICKY CONSTRUCTION CORP.
A PROUD MEMBER OF THE J.A. COLLINS™ COMPANIES

An Equal Opportunity Employer

Rutland City BRF 3000 (2014036)
SUBMITTAL 6

Issued 11/07/14
Respond by 11/12/14

To

Timothy Pockette, PE

Topic Geotextile for Silt Fence
Status For Approval
Spec section 649.51
Sent to approver 11/7/14

From

HARPER T CALLAHAN

Signed by 

Date 11/7/14

Proceed as Indicated _____
Owner Authorized Representative

Date _____

Indian Valley Industries, Inc.

Technical Data Sheet

IVI 3617 Silt Fence VT AOT

3' X 100' – 6' Stake Spacing
1.25" x 1.25" x 48" Pointed Hardwood Stakes

This is to certify that IVI 3617 Silt Fence will meet or exceed the following typical values when tested in accordance with the proper ASTM test method. Complies to AASHTO specification M-288.

TEST RESULTS		
PHYSICAL PROPERTY	TEST METHOD	TYPICAL VALUE
Composition		Polypropylene
Weight	ASTM D5261	3.1 oz sq yd
Color		Black
Tensile Strength – Warp x Fill	ASTM D4632/D1682	124 lbs. x 124 lbs.
Elongation - Warp x Fill	ASTM D4632	18% x 18%
Trapezoid Tear – Warp x Fill	ASTM D4533	75 lbs. x 75 lbs.
Flow Rate	ASTM D4491	10 gal/min/sf
Puncture Strength	ASTM D4833	65 lbs.
Mullen Burst	ASTM D3786	300 psi
Apparent Opening Size	ASTM D4751	.60mm(30 US Sieve)
Permittivity	ASTM D4491	0.15 1/Sec
Permeability	ASTM D4491	.006 cm/s
UV Resistance After 500 Hrs	ASTM D4355	80%
Test results represent Minimum Average Roll Values (MARV) with the exception of weight which is a typical result.		

THE INFORMATION PRESENTED HEREIN, WHILE NOT GUARANTEED, IS TO THE BEST OF OUR KNOWLEDGE TRUE AND ACCURATE. EXCEPT WHEN AGREED TO IN WRITING FOR SPECIFIC CONDITIONS OF USE, NO WARRANTY OR GUARANTEE EXPRESSED OR IMPLIED IS MADE REGARDING THE PERFORMANCE OF ANY PRODUCT, SINCE THE MANNER OF USE AND HANDLING ARE BEYOND OUR CONTROL. NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS PERMISSION OR AS A RECOMMENDATION TO INFRINGE ANY PATENT.